## Biaxial Geogrid GG 1200



KEYMAY's Biaxial Geogrid is an integrally formed structure, which especially designed for soil stabilization and reinforcement application. KEYMAY's Biaxial Geogrid is manufactured from Polypropylene, from the process of extruding, longitudinal stretching and transverse stretching.

KEYMAY's Biaxial Geogrid features high tensile strength at both longitudinal (MD) and transverse (TD) directions. It makes soil reinforced with its excellent structure stability and strong mechanical interlock performance.

## **APPLICATIONS**

- Base reinforcment
- Subgrade reinforcement
- Slope reinforcement
- · Embankment stabilization

PROPERTIES	TEST METHOD	UNIT	MD Values	TD Values
INDEX PROPERTIES				
Polymer	-	-	PP	-
Minimum Carbon Black	ASTM D-4218	%	2	-
Tensile Strength @ 2% Strain	ASTM D-6637	KN/m (lb/ft)	6 (410)	9 (620)
Tensile Strength @ 5% Strain	ASTM D-6637	KN/m (lb/ft)	11.8 (810)	19.6 (1,340)
Ultimate Tensile Strength	ASTM D-6637	KN/m (lb/ft)	19.2 (1,310)	28.8 (1,970)
STRUCTURAL INTEGRITY				
Junction Efficiency	GRI GG2	%	93	93
Flexural Rigidity	ASTM D-7748	mg-cm	750,000	-
Aperture Stability	ASTM D-7864	m-N/deg	0.65	-
DIMENSIONS				
Aperture Dimensions	-	mm (in)	26 (1.0)	34 (1.3)
Minimum Rib Thickness	ASTM D-1777	mm (in)	1.6 (0.06)	1.1 (0.04)
Roll Width	-	m (ft)	3.95 (12.9) or 5.95 (19.5)	-
Roll Length	-	m (ft)	50 (164)	-

© KEYMAY Industries Inc. This publication should not be construed as engineering advice. While the information contained in this publication is accurate to the best of our knowledge, this information is provided for reference purposes only and is not intended as a warranty or guarantee. KEYMAY assumes no liability in connection with the use of this information. Specifications subject to change without notice. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use.

PDS-007-GG1100 REV 0 (2023)